



PRESSIZA 91

PERFORMANCE GUIDE

Features

- Clear biaxially oriented propylene overlamine
- High grade clear emulsion acrylic
- Excellent acid, chemical, oil and scuff resistance
- Industry standard for general purpose label protection

Regulatory Compliance:

RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, CEPA, CONEG, FDA 21 CFR 175.105, 21CFR177.1520(c) (1.1) & (3.1). California Proposition 65

Face

Caliper 0.0075 +/- 10% inches

Adhesive

Thickness 0.3 +/- 10% inches

Peel Adhesion: Steel

13 oz/in 30 min conditioning

16 oz/in 24 hr conditioning

Temperature Ranges

Minimum Application 32°F (°C)

Service Ranges 0°F to 180°F (-18°C to 82°C)

Roll Tolerances

Roll Length +/- 5%

Roll Width +/- 0.0625 in (1/16 in)

Shelf Life

Two years when stored at 70°F and 50% relative humidity
Rolls must be transported and stored on protected surfaces
Use caution when placing or removing roll from mandrel



rsimexico.com



Contacto

contacto@rsimexico.com
Teléfono Tijuana: 664-215-0679
Teléfono Puebla: 222-225-6594

