



# PRESSIZA 23

## PERFORMANCE GUIDE

### Features

- A 0.000225" aluminum foil laminated to a white kraft base sheet, with an acrylic topcoating for printability
- Rubberbased adhesive featuring high initial tack and ultimate bond strength to a wide variety of substrates, including low surface energy plastics, treated glass, and corrugated cardboard
- Features excellent high speed/wide web converting characteristics
- Bleached supercalendered kraft stock featuring high internal strength, toughness, and tear resistance. Used primarily for roll-to-roll label applications

### Face

Caliper 0.0037 +/- 10% inches

### Adhesive

Thickness 1.0 mils  
Peel Adhesion Glass PE treated: 2.34 lbs

---

#### Temperature Ranges

Minimum Application +25° F (-4°C)  
Service Ranges -65° F to +160° F (-54°C to 71°C)

### Liner

Caliper 0.0025 +/- 10% inches  
Basis Weight 42 per ream +/- 10%  
(24" x 36" 500 sheets)

### Shelf Life

Unless specified otherwise in this document, one year when stored at 72°F at 50% RH

### Suggested applications

Good printing with solvent/waterbased Flexo. Not recommended for imprinting.

### Important:

Suitable for applications where compliance with FDA 175.105 is required. This section covers applications where incidental contact between food and adhesive could occur.



[rsimexico.com](http://rsimexico.com)



#### Contacto

contacto@rsimexico.com  
Teléfono Tijuana: 664-215-0679  
Teléfono Puebla: 222-225-6594

