

# **Z-Supreme 3000T**

# **FEATURES**

- Thermal transfer, white, matte polyimide label with a high-temp permanent acrylic adhesive
- Excellent smear/scratch resistance
- Unparalleled durability and chemical resistance
- May be used in wave solder processes for printed circuit boards
- Available in white (65080RM)

# **MATERIAL CONSTRUCTION**

| Component | Description                       | Caliper |
|-----------|-----------------------------------|---------|
| Facestock | White, matte coated polyimide     | 2.2 mil |
| Adhesive  | High-temperature, acrylic-based   | 1.2 mil |
| Liner     | 50 lb. semi-bleached, kraft stock | 3.0 mil |
|           | TOTAL ± 10%                       | 6.4 mil |

# **Time/Temperature Performance**

| Temperature    | Time      |  |
|----------------|-----------|--|
| 1000 F (583 C) | 5 seconds |  |
| 662 F (350 C)  | 2 minutes |  |
| 626 F (330 C)  | 5 minutes |  |
| 500 F (260 C)  | 2 hours   |  |
|                |           |  |

### TEMPERATURE PERFORMANCE

| Minimum<br>Application<br>Temperature | Service<br>Temperature                 | Optimal<br>Storage<br>Conditions |
|---------------------------------------|--|----------------------------------|
| 50° F (10° C)                         | -40° F to 482° F<br>(-40° C to 250° C) | 72° F (22° C)<br>at 50% RH       |

# **Expected Exterior Life** 2 years

### CHEMICAL RESISTANCE

|          | Chemical       | Suggested Ribbon<br>5100 |
|----------|----------------|--------------------------|
|          | Blood          | •                        |
| J        | Body Fluid     | •                        |
| Weak     | Salt Water     | •                        |
|          | Water          | •                        |
|          | Window Cleaner | •                        |
| _        | Alcohol        | •                        |
| erate    | Ammonia        | •                        |
| Moderate | Bleach         | •                        |
|          | IPA            | •                        |
|          | Gasoline       |                          |
| Harsh    | Grease         |                          |
|          | Oil            |                          |
| Extreme  | Acetone        | NR                       |
|          | IR Reflow      | NR                       |
|          | MEK            | NR                       |
|          | TCE            | NR                       |
|          | Xylene         | NR                       |

Recommended ○ Test in Your Application NR Not Recommended

#### **SUGGESTED APPLICATIONS**

Bottom-side lead-free PCB labeling



Product identification



Automotive labeling



Extreme high temperature applications up to 482°F



All products should be pre-tested to ensure it meets all intended requirements of specific end-use applications.

# For more information, visit www.zebra.com/supplies

Product Performance and Suitability: The information contained in this document is to be used for guidance only and is not intended for use in setting specifications. All purchasers of Zebra products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application.

NA and Corporate Headquarters | +1 800 423 0442 | inquiry4@zebra.com

©2018 ZIH Corp and/or its affiliates. All rights reserved. ZEBRA and the stylized Zebra head are trademarks of ZIH Corp, registered in many jurisdictions worldwide. All other trademarks

are the property of their respective owners











