

PRESSIZA 53

PERFORMANCE GUIDE

Features

- Bleached, super calendered paper stock with very good diecutting and matrix stripping properties
- Used for standard roll-to-roll applications. Not recommended for sheeting
- Opaque white facestock with very good hiding power and physical strength
- Semigloss surface treatment accepts most flexographic, letterpress, and rotary screen inks
- Good thermal transfer printability with most wax/resin and resin based ribbons
- Excellent removability from most substrates up to 6 to 12 months

Face

Caliper 0.0020 +/- 10% inches

Adhesive

Thickness 0.0009 +/- 10% inches

Peel Adhesion Stainless Steel: 20.0 oz/in

Temperature Ranges

Minimum Application +50°F (10°C)

Service Ranges -40°F to 250°F (-40°C to 121°C)

Liner

Caliper 0.0032 +/- 10% inches

Basis Weight 54.5 lbs.
(24" x 36" 500 sheets)

Shelf Life

Unless otherwise specified in this document, ideally store at 72°F and 50% RH

Suggested applications

- Product identification labels
- Barcode labels
- Rating plates
- Work in process (WIP) or other temporary label
- Durable goods protect film
- UL component labels

Important:

The substances listed in article 4 lid 1 of 2002/95/EU (RoHS) are not intentionally used in this product. The concentration limits of these substances will not exceed the set maximum concentration limits as provided in the proposed amendment for 2002/95/EU.

