

PRESSIZA 92

PERFORMANCE GUIDE



Features

- Thermal transfer printable polypropylene overlamine
- Excellent acid, chemical, oil and scuff resistance
- Designed for thermal transfer, hot foil stamp and Videojet® printability
- Specific ribbon testing required
- Ideal for bar code or other variable information applications

Regulatory Compliance:

RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, CEPA, CONEG, FDA 21 CFR 175.105, 21CFR177.1520(c) (1.1) & (3.1). California Proposition 65

Face

Caliper 1.0 mil

Adhesive

Thickness 0.3 +/- 10% inches

Peel Adhesion: Steel
13 oz/in 30 min conditioning
16 oz/in 24 hr conditioning

Temperature Ranges

Minimum Application 32°F (°C)
Service Ranges 0°F to 180°F (-18°C to 82°C)

Roll Tolerances

Roll Length +/- 5%
Roll Width +/- 0.0625 in (1/16 in)

Shelf Life

Two years when stored at 70°F and 50% relative humidity
Rolls must be transported and stored on protected surfaces
Use caution when placing or removing roll from mandrel

This information is confidential, and restricted for the internal use of RSI México customers for informative purposes, and can not be reproduced or communicated to third parties without our written authorization.

TIJUANA: (664) 215.0679

PUEBLA: (222) 225.6594

HERMOSILLO: (662) 369.7306

comunicacion@rsimexico.com

